

Product Information: menzolit[®] BMC 3100

Issued: 21/03/2014



TYPICAL APPLICATION



PRODUCT DESCRIPTION

menzolit[®] BMC 3100 is a bulk moulding compound based on unsaturated polyester resin. The product is glass fibre reinforced and contains mineral fillers. In case of fire the product doesn't melt, neither does it form droplets nor is smoke generation excessive. The material is injection moulded in heated steel moulds. It is recommended to work with chrome plated tools. It does not contain any halogens nor any candidates from the REACH SVHC list.

PRODUCT SPECIFICATION

BMC for headlamp reflectors.

TYPICAL PROPERTIES

	Standard	Units	
Density	ISO 1183	g/cm³	2,0
Shrinkage	ISO 2577	%	0,00
Heat Distortion Temp.	EN ISO 75-2	°C	>200
Continuous Service Temp.	Menzolit	°C	190
Young's Modulus	EN ISO 527-4	GPa	14
Tensile Strength	EN ISO 527-4	MPa	25
Flexural Strength	EN ISO 14125	MPa	100
Flex Modulus	EN ISO 14125	GPa	12
Impact Strength	EN ISO 179	kJ/m²	15
Glow Wire Index	IEC 60707-3	°C	
Fire Retardancy	UL 94		
Surface Resistivity	IEC 60093	Ohm	10 ¹²
Comparative Tracking Index	IEC 60112	Level	CTI600
Water Absorption	ISO 62	%	< 0,5

FORM of SUPPLY

menzolit[®] BMC 3100 is packaged in styrene tight bags and placed in cardboard or wooden boxes. Various kinds of packaging available. For alternative packaging please contact our technical service team. Available in limited colours.

menzolit[®] is a registered trademark.

Properties given are the mean value of test results, and taken from non pigmented, compression moulded panels at room temperature. Our products are manufactured according to ISO 9000 standards, a Safety Data Sheet according to EG No. 1907/2006/CE is available. Notice: We make no warranty or representation as to the suitability of the product or information herein for any particular application. The determination of the suitability of the above information please contact your local Menzolit Technical Service Team for assistance or see www.menzolit.com.